


Claims:

- 1) A process for preparing disazo pigments of the formula (I)



or a mixture of said disazo pigments by azo coupling, where

R^1 and R^2 are identical or different and are hydrogen, C_1 - C_4 alkyl, C_1 - C_4 alkoxy, C_1 - C_5 alkoxy carbonyl, nitro, cyano, halogen, phenoxy or trifluoromethyl;

D^1 and D^2 are identical or different and are an aromatic heterocycle from the group consisting of benzimidazole, benzimidazolone, benzimidazolethione, benzoxazole, benzoxazolone, benzothiazolone, indazole, phthalimide, naphthalimide, benzotriazole, quinoline, benzodiazines, phenmorpholine, phenmorpholinone, benzo[c,d]indolone, benzimidazo[1,2-a]pyrimidone, carbazole and indole, said heterocycles being unsubstituted or substituted by 1, 2, 3 or 4 identical or different radicals from the group consisting of halogen, C_1 - C_4 alkyl, acetamido, carbomethoxyamino, C_1 - C_4 alkoxy, nitro, phenyl, phenoxy or trifluoromethyl, it being possible for the phenyl radical to be substituted by chloro, methyl or methoxy, and said heterocycle being attached directly or via a phenylene group to the azo group in formula (I),

which comprises subjecting the azo coupling product to a finish in organic solvent in the presence of a base from the group consisting of alkali metal hydroxides and alkali metal alkoxides or in aqueous-organic solvent at alkali $pH \geq 9$.

2) The process as claimed in claim 1, wherein R¹ and R² are identical or different and are hydrogen, methyl, ethyl, methoxy, ethoxy, propoxy, butoxy, fluoro, chloro, bromo, cyano, nitro, methoxycarbonyl, ethoxycarbonyl or trifluoromethyl.

5

3) The process as claimed in claim 1, wherein the aromatic heterocycle is a benzimidazolone, phthalimide, naphthalimide, quinazoline, quinazolinone, quinazolinedione, phthalazine, phthalazinone, phthalazinedione, quinoxaline, quinoxalinone or quinoxalinedione.

10

4) The process as claimed in one or more of claims 1 to 3, wherein the heterocycles D¹ and D² are unsubstituted or substituted by 1, 2 or 3 identical or different radicals from the group consisting of methyl, ethyl, methoxy, ethoxy, nitro, fluoro, chloro, bromo, phenyl or trifluoromethyl.

15

5) The process as claimed in one or more of claims 1 to 4, wherein the coupling product is used in the form of a presscake, as granules or as powder.

6) The process as claimed in one or more of claims 1 to 5, wherein the coupling product is finished in a suspension containing from 1 to 50% by weight, preferably from 2 to 20% by weight, in particular from 3 to 17.5% by weight of the coupling product, based on the total weight of the suspension.

7) The process as claimed in one or more of claims 1 to 6, wherein the organic solvent for the finish is an alcohol having 1 to 20 carbon atoms, a glycol, glycerol, a polyglycol, an ether, a glycol ether, a ketone, an aliphatic acid amide, a urea derivative, a cyclic carboxamide, an ester of an aliphatic or aromatic carboxylic acid, a nitrile, an aliphatic, aromatic or araliphatic hydrocarbon, an alkyl-, alkoxy-, nitro-, and/or halogen-substituted benzene, an aromatic heterocycle, hexamethylphosphoramide, 1,3-dimethyl-2-imidazolidinone; a sulfone, a sulfoxide; or a mixture of these solvents

8) The process as claimed in one or more of claims 1 to 7, wherein the organic solvent for the finish is a C₁-C₆ alcohol, particularly methanol, ethanol, isopropanol, isobutanol, tert.-butanol or tert.-amyl alcohol, or butyl glycol, dimethylformamide, N,N-dimethylacetamide, N-methylpyrrolidone or dimethylsulfoxide, or a mixture thereof.

5

9) The process as claimed in one or more of claims 1 to 8, wherein the aqueous-organic solvent contains from 2.5 to 95% by weight, preferably from 5 to 90% by weight, of organic solvent.

10

10) The process as claimed in one or more of claims 1 to 9, wherein the finish takes place at an alkali pH of greater than 9.5.

11) The process as claimed in one or more of claims 1 to 10, wherein the finish is carried out at a temperature of between 0 and 250°C, preferably between 15 and 200°C.

15

12) The process as claimed in one or more of claims 1 to 11, wherein the finish is carried out for a time of from 5 minutes to 96 hours.

20

13) The process as claimed in one or more of claims 1 to 12, wherein following a finish at alkali pH an acid is added.